


KEY QUARTZ B-125

Technical Data Sheet



DESCRIPTION

KEY QUARTZ B-125 is a 1/8" decorative resin flooring system consisting of clear, 100% solids, epoxy resin and colored quartz aggregate. This durable quartz system is finished with various options of clear epoxy, polyaspartic or urethane resins, in satin or gloss to meet project requirements. The installed system can be textured or smooth as desired. Ease of cleaning and maintenance minimizes bacterial growth. The decorative quartz aggregate is available in a series of pre-blended patterns or solid colors. Crack-resistant installations of **KEY QUARTZ B-125** can be achieved when installed in conjunction with **KEY #580 Waterproofing and Crack Isolation Membrane**. An integral cove base can be installed in areas requiring seamless floor to wall finishes. For high chemical resistant applications specify **KEY QUARTZ B-125-HP** or **KEY RESISTANT QUARTZ B-125**.

KEY ADVANTAGES

- Decorative appearance
- High wear, impact, and abrasion resistance
- Low maintenance
- Safe (slip resistant finish)
- Chemical resistant finishes are available
- Meets USGBC LEED criteria for low VOC
- Meets USDA requirements
- Available with Bioclean antimicrobial additive if needed

TYPICAL USES

- Corridors
- Restrooms and locker rooms
- Kitchen areas
- Food and beverage processing
- Classrooms
- Shower rooms
- Cafeterias
- Laboratories
- Animal housing
- Production, manufacturing areas
- Clean rooms
- Government and military facilities
- Healthcare facilities
- Numerous other uses—consult with **Key Resin**

PHYSICAL PROPERTIES

| Test Name | Method | Value |
|-------------------------------------|--------------------------------------|---|
| Color | | Key Standard Colors and Custom Colors |
| VOC (Volatile Organic Content) | EPA Method 24 | Refer to Individual Product Component Data Sheet |
| Adhesion to Concrete | ASTM D7234 | 300-400+ psi (Concrete Failure, varies by concrete strength) |
| Compressive Strength | ASTM C579 | 12,600 psi |
| Flexural Strength | ASTM C580 | 4,300 psi |
| Hardness, Shore D | ASTM D2240 | 80-84 |
| Tensile Strength | ASTM C307 | 2,600 psi |
| Flammability | ASTM D635 | Self Extinguishing |
| Impact Resistance | MIL-D-3134J | Withstands 16 ft-lbs without cracking, delamination or chipping |
| Abrasion Resistance | ASTM D-4060, CS17 Wheel, 1000 cycles | 32 mg average Varies by topcoat |
| Resistance to Elevated Temperatures | MIL-D-3134J | No slip or flow at required temperature of 158°F |
| Slip Resistance | ASTM D2047 | >0.6 Passes ADA recommendations |

KEY QUARTZ B-125

Technical Data Sheet



APPLICATION

SURFACE PREPARATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared and tested for moisture as outlined in **Key Resin Technical Bulletin #1**. If moisture testing confirms excessive levels of moisture, apply moisture mitigation system recommended by **Key Resin**. Work must be performed by experienced contractors. The **Key Resin Technical Service Department** is available to answer any questions.

INSTALLATION

KEY QUARTZ B-125 material components are mixed on site. Refer to the detailed installation instructions document and **Key Resin Technical Service**.

CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with xylene or lacquer thinner. Consult Safety Data Sheet (SDS) for safety and health precautions.

MAINTENANCE

After completing the application of **KEY QUARTZ B-125**, the installer should provide the owner with maintenance instructions. **KEY QUARTZ B-125** is easily cleaned with neutral soaps or detergents. Routine mechanical scrubbing using the appropriate pad is recommended for all surfaces having a slip resistant texture. Refer to **Key Resin Technical Bulletins #3 and #3-A** for additional recommendations.

SYSTEM OPTIONS

- Fast cure formulations
- UV light resistance formulations
- Cold cure formulations
- Urethane, polyaspartic finishes
- Chemical resistant finishes
- Crack-isolation flexible membrane
- Moisture tolerant base coats

TECHNICAL SERVICE

Key Resin Company provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces. **Key Resin Sales/Technical Representatives** are available to assist. Telephone 888.943.4532 or visit www.keyresin.com.

AVAILABILITY

Key Resin materials are available throughout the United States, Canada, China, and a number of other countries. Contact the **Key Resin Representative** in your area for details.

WARRANTY

Key Resin Company ("Key") warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed, and applied in accordance with recommendations of Key. If any product fails to meet this warranty, the liability of Key will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Key within (1) one year of delivery of materials. Key may in its discretion refund the price received by Key in lieu of replacing the material. No customer, distributor, or representative of Key is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Key. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Key reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. KEY'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND KEY SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Rev 6/26/2020 v1.0